

AS1420 (1074)
1-Part heat cured thermally conductive adhesive

Introduction

AS1420 is a grey viscous liquid, which is a self-bonding silicone sealant using addition cure technology. The single part silicone will cure to a tough silicone elastomer by heating to temperatures above 100°C.

AS1420 has a completely neutral curing system that makes it suitable for applications where non-corrosive properties and primerless adhesion are prerequisite.

Key Features

- Fast elevated temperature cure
- Excellent thermal conductivity
- Non corrosive
- Tough, protective rubber

Use and Cure Information

How to Use

AS1420 is ready to use 1 part system. It is recommended that liquid versions be thoroughly mixed prior to use particularly thermally conductive products.

Ensure that all surfaces to be brought into contact with AS1420 are clean and degreased. The work area should be free of contaminants such as organic compounds of sulphur, phosphorus, nitrogen and tin, which act as catalyst poisons.

Application and Cure

The rate of cure will depend on how long it takes for the sealant to reach the required curing temperature. Small beads of 1 to 2mm diameter, used as formed-in-place gaskets, can be cured quickly with hot air guns e.g. paint stripper types.

The table shown below offers a guide to the curing conditions observed for 20g to 50g of AS1400 in 5 to 10mm sections. All times are based on the actual time in an air-circulating oven at the stated temperature.

Note: Improved adhesion is achieved by post cure at 120 to 150°C for 1 to 2 hours.

<u>Oven temperature, °C</u>	<u>Time, minutes</u>
100	20 to 30
120	15 to 20
150	10 to 15
175	1 to 5

The information and recommendations in this publication are to the best of our knowledge reliable. However nothing herein is to be construed as a warranty or representation. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.

ACC Silicones Ltd, Amber House,
Showground Road, Bridgwater, Somerset, UK
Tel. +44(0)1278 411400 Fax. +44(0)1278 411444

Property

Test Method

Value

Uncured Product

Colour:		Grey
Appearance:		Viscous liquid.
Viscosity:	Brookfield	43000 mPa.s

Cured Elastomer

(after 60 minutes at 120°C on a 3 mm test sheet)

Tensile Strength:	BS903 Part A2	3.10 MPa
Elongation at Break:	BS903 Part A2	70 %
Hardness:	ASTM D 2240-95	67° Shore A
Specific Gravity:	BS 903 Part A1	2.06
Linear Shrinkage:		2.00 %
Thermal Conductivity:		1.38 W/mK
Coefficient of Thermal Expansion:		
Volumetric		562 ppm / °C
Linear		187 ppm / °C
Min. Service Temperature:		-50 °C
Max. Service Temperature:	AFS 1540B	260 °C

Electrical Properties

Volume Resistivity:	ASTM D-257	7.7E +15 Ω.cm
Surface Resistivity:	ASTM D-257	1.3E+15 Ω
Dielectric Strength:	ASTM D-149	22.5 kV/mm
Dielectric Constant at 50Hz:	ASTM D-150	6.00

Adhesion

Customers are advised to carry out their own tests on clean, degreased substrates to ensure satisfactory adhesion is achieved

All values are typical and should not be accepted as a specification.

Health and Safety – Material Safety Data Sheets available on request.

Packages –1 kg containers. Arrangements can be made to supply in bulk containers.

Storage and Shelf Life - Expected to be 6 months in original, unopened containers at temperatures below 15°C

Revision Date: 25.01.2012

Treco S.R.L., Via Romagna N.8,
20098 Sesto Ulteriano (MI), Italia.
Tel. 39/02/9880913 Fax. +39/02/98280413